

Aluminium Titanate

Items	Datas
Bulk Density	3.3-3.5g/cm ³
Flexural Strength	30-50Mpa
Porosity	<8%
Thermal-expansion coefficient	0.5-1.5*10 ⁻⁶ °C
Heat Conductivity (800°C)	0.86W/m.K



: +90 850 305 93 30



: info@hekmetal.com



: www.hekmetal.com



Şerifali Mah. İbrahim Hakkı Sk. Nish Palace
Blok No: 40 İç Kapı No:1 Ümraniye/İSTANBUL



Vergi Dairesi : Sarıgazi

Vergi No : 4610928910

Mersis No : 0461092891000001