

## 1、 Product Name:

### Aluminium Silicate Bushing

## 2、 Performance index:

Items	Datas
Al <sub>2</sub> O <sub>3</sub> content:	50-51%
SiO <sub>2</sub> content:	48-49%
Slag content:	<0.06%
Burning loss:	<1.1%
Density:	0.4-0.5g/cm <sup>3</sup>
Thermal coefficient:	<0.12W/m.k (700°C)
Bending strength:	≥0.05Mpa
Compression strength:	≥0.15Mpa
Continuous working temp:	800°C
Max working temp:	1250°C